

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Air-Pro® (PE)	1-1/2" (50mm) SDR7	33.7 lbs	1 mm	Almost Zero	69 seconds	6 seconds	33.7 lbs	7.4 min
Air-Pro® (PE)	2" (63mm) SDR7	51.7 lbs	1.5 mm	Almost Zero	86 seconds	7 seconds	51.7 lbs	8.9 min
Air-Pro® (PE)	3" (90mm) SDR7	103.4 lbs	2 mm	Almost Zero	123 seconds	8 seconds	103.4 lbs	12.3 min
Air-Pro® (PE)	4" (110mm) SDR7	152.9 lbs	2 mm	Almost Zero	151 seconds	9 seconds	152.9 lbs	14.8 min
Air-Pro® (PE)	6" (160mm) SDR11	227.1 lbs	2 mm	Almost Zero	146 seconds	9 seconds	227.1 lbs	14.2 min
Asahitec™ Solid Wall (PP-RCT)	1-1/2" (50mm) SDR11	15.7 lbs	0.5 mm	Almost Zero	54 seconds	5 seconds	15.7 lbs	5.1 min
Asahitec™ Solid Wall (PP-RCT)	2" (63mm) SDR11	24.7 lbs	0.5 mm	Almost Zero	68 seconds	6 seconds	24.7 lbs	6.3 min
Asahitec™ Solid Wall (PP-RCT)	2-1/2" (75mm) SDR11	33.7 lbs	0.5 mm	Almost Zero	79 seconds	6 seconds	33.7 lbs	7.3 min
Asahitec™ Solid Wall (PP-RCT)	3" (90mm) SDR11	49.5 lbs	1 mm	Almost Zero	94 seconds	6 seconds	49.5 lbs	8.6 min
Asahitec™ Solid Wall (PP-RCT)	4" (110mm) SDR11	71.9 lbs	1 mm	Almost Zero	113 seconds	7 seconds	71.9 lbs	10.2 min
Asahitec™ Solid Wall (PP-RCT)	5" (125mm) SDR11	92.2 lbs	1 mm	Almost Zero	129 seconds	7 seconds	92.2 lbs	11.5 min
Asahitec™ Solid Wall (PP-RCT)	6" (160mm) SDR11	150.6 lbs	1 mm	Almost Zero	161 seconds	8 seconds	150.6 lbs	14.2 min
Asahitec™ Solid Wall (PP-RCT)	1-1/2" (50mm) SDR7	22.5 lbs	0.5 mm	Almost Zero	80 seconds	6 seconds	22.5 lbs	7.4 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Asahitec™ Solid Wall (PP-RCT)	2" (63mm) SDR7	33.7 lbs	1 mm	Almost Zero	98 seconds	6 seconds	33.7 lbs	8.9 min
Asahitec™ Solid Wall (PP-RCT)	2-1/2" (75mm) SDR7	47.2 lbs	1 mm	Almost Zero	117 seconds	7 seconds	47.2 lbs	10.5 min
Asahitec™ Solid Wall (PP-RCT)	3" (90mm) SDR7	69.7 lbs	1 mm	Almost Zero	138 seconds	7 seconds	69.7 lbs	12.3 min
Asahitec™ Solid Wall (PP-RCT)	4" (110mm) SDR7	103.4 lbs	1 mm	Almost Zero	166 seconds	8 seconds	103.4 lbs	14.7 min
Asahitec™ Solid Wall (PP-RCT)	5" (125mm) SDR7	130.4 lbs	1 mm	Almost Zero	187 seconds	8 seconds	130.4 lbs	16.4 min
Chem Proline® (PE)	1-1/2" (50mm) SDR11	22.5 lbs	1 mm	Almost Zero	46 seconds	5 seconds	22.5 lbs	5.1 min
Chem Proline® (PE)	2" (63mm) SDR11	36.0 lbs	1 mm	Almost Zero	58 seconds	6 seconds	36.0 lbs	6.3 min
Chem Proline® (PE)	3" (90mm) SDR11	71.9 lbs	1.5 mm	Almost Zero	82 seconds	6 seconds	71.9 lbs	8.6 min
Chem Proline® (PE)	4" (110mm) SDR11	107.9 lbs	1.5 mm	Almost Zero	100 seconds	7 seconds	107.9 lbs	10.2 min
Chem Proline® (PE)	6" (160mm) SDR11	227.1 lbs	2 mm	Almost Zero	146 seconds	9 seconds	227.1 lbs	14.2 min
Climatec™ (PP-RCT)	1-1/2" (50mm) SDR11	15.7 lbs	0.5 mm	Almost Zero	54 seconds	5 seconds	15.7 lbs	5.1 min
Climatec™ (PP-RCT)	2" (63mm) SDR11	24.7 lbs	0.5 mm	Almost Zero	68 seconds	6 seconds	24.7 lbs	6.3 min
Climatec™ (PP-RCT)	2-1/2" (75mm) SDR11	33.7 lbs	0.5 mm	Almost Zero	79 seconds	6 seconds	33.7 lbs	7.3 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Climatec™ (PP-RCT)	3" (90mm) SDR11	49.5 lbs	1 mm	Almost Zero	94 seconds	6 seconds	49.5 lbs	8.6 min
Climatec™ (PP-RCT)	4" (110mm) SDR11	71.9 lbs	1 mm	Almost Zero	113 seconds	7 seconds	71.9 lbs	10.2 min
Climatec™ (PP-RCT)	5" (125mm) SDR11	92.2 lbs	1 mm	Almost Zero	129 seconds	7 seconds	92.2 lbs	11.5 min
Climatec™ (PP-RCT)	6" (160mm) SDR17	101.2 lbs	1 mm	Almost Zero	108 seconds	6 seconds	101.2 lbs	9.8 min
Proline® PRO150 (PP)	1-1/2" (50mm) SDR11	15.7 lbs	0.5 mm	Almost Zero	54 seconds	5 seconds	15.7 lbs	5.1 min
Proline® PRO150 (PP)	2" (63mm) SDR11	24.7 lbs	0.5 mm	Almost Zero	68 seconds	6 seconds	24.7 lbs	6.3 min
Proline® PRO150 (PP)	2-1/2" (75mm) SDR11	33.7 lbs	0.5 mm	Almost Zero	79 seconds	6 seconds	33.7 lbs	7.3 min
Proline® PRO150 (PP)	3" (90mm) SDR11	49.5 lbs	1 mm	Almost Zero	94 seconds	6 seconds	49.5 lbs	8.6 min
Proline® PRO150 (PP)	4" (110mm) SDR11	71.9 lbs	1 mm	Almost Zero	113 seconds	7 seconds	71.9 lbs	10.2 min
Proline® PRO150 (PP)	4-1/2" (125mm) SDR11	92.2 lbs	1 mm	Almost Zero	129 seconds	7 seconds	92.2 lbs	11.5 min
Proline® PRO150 (PP)	5" (140mm) SDR11	114.7 lbs	1 mm	Almost Zero	142 seconds	7 seconds	114.7 lbs	12.6 min
Proline® PRO150 (PP)	6" (160mm) SDR11	150.6 lbs	1 mm	Almost Zero	161 seconds	8 seconds	150.6 lbs	14.2 min
Proline® PRO45 (PP)	4" (110mm) SDR33	27.0 lbs	0.5 mm	Almost Zero	40 seconds	5 seconds	27.0 lbs	5.0 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Proline® PRO45 (PP)	4-1/2" (125mm) SDR33	33.7 lbs	0.5 mm	Almost Zero	46 seconds	5 seconds	33.7 lbs	5.0 min
Proline® PRO45 (PP)	5" (140mm) SDR33	42.7 lbs	0.5 mm	Almost Zero	51 seconds	5 seconds	42.7 lbs	5.0 min
Proline® PRO45 (PP)	6" (160mm) SDR33	54.0 lbs	0.5 mm	Almost Zero	57 seconds	5 seconds	54.0 lbs	5.4 min
Super Proline® (PVDF)	1-1/2" (50mm) SDR21	10.0 lbs	0.5 mm	Almost Zero	70 seconds	3 seconds	10.0 lbs	5.5 min
Super Proline® (PVDF)	2" (63mm) SDR21	13.0 lbs	0.5 mm	Almost Zero	70 seconds	3 seconds	13.0 lbs	5.5 min
Super Proline® (PVDF)	2-1/2" (75mm) SDR21	18.0 lbs	0.5 mm	Almost Zero	76 seconds	3 seconds	18.0 lbs	6.5 min
Super Proline® (PVDF)	3" (90mm) SDR21	26.0 lbs	0.5 mm	Almost Zero	83 seconds	3 seconds	26.0 lbs	7.0 min
Super Proline® (PVDF)	4" (110mm) SDR21	38.0 lbs	0.5 mm	Almost Zero	93 seconds	3 seconds	38.0 lbs	8.5 min
Super Proline® (PVDF)	6" (160mm) SDR21	81.0 lbs	0.7 mm	Almost Zero	117 seconds	4 seconds	81.0 lbs	11.0 min
Super Proline® (PVDF)	3" (90mm) SDR33	17.0 lbs	0.5 mm	Almost Zero	68 seconds	3 seconds	17.0 lbs	5.5 min
Super Proline® (PVDF)	4" (110mm) SDR33	25.0 lbs	0.5 mm	Almost Zero	74 seconds	3 seconds	25.0 lbs	6.0 min
Super Proline® (PVDF)	6" (160mm) SDR33	52.0 lbs	0.5 mm	Almost Zero	89 seconds	3 seconds	52.0 lbs	8.0 min
Ultra Proline® (ECTFE)	1-1/2" (50mm) SDR21	9.0 lbs	0.5 mm	Almost Zero	25 seconds	4 seconds	9.0 lbs	5.0 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Ultra Proline® (ECTFE)	2" (63mm) SDR21	11.0 lbs	0.5 mm	Almost Zero	25 seconds	4 seconds	11.0 lbs	5.0 min
Ultra Proline® (ECTFE)	3" (90mm) SDR21	22.0 lbs	0.5 mm	Almost Zero	34 seconds	4 seconds	22.0 lbs	6.0 min
Ultra Proline® (ECTFE)	4" (110mm) SDR21	33.0 lbs	0.5 mm	Almost Zero	40 seconds	4 seconds	33.0 lbs	7.0 min
Ultra Proline® (ECTFE)	6" (160mm) SDR21	81.0 lbs	1 mm	Almost Zero	117 seconds	4 seconds	81.0 lbs	11.0 min
Watertec™ (PP-RCT)	1-1/2" (50mm) SDR9	18.0 lbs	0.5 mm	Almost Zero	65 seconds	5 seconds	18.0 lbs	6.1 min
Watertec™ (PP-RCT)	2" (63mm) SDR9	29.2 lbs	1 mm	Almost Zero	82 seconds	6 seconds	29.2 lbs	7.6 min
Watertec™ (PP-RCT)	2-1/2" (75mm) SDR9	40.5 lbs	1 mm	Almost Zero	96 seconds	6 seconds	40.5 lbs	8.7 min
Watertec™ (PP-RCT)	3" (90mm) SDR9	58.5 lbs	1 mm	Almost Zero	114 seconds	7 seconds	58.5 lbs	10.3 min
Watertec™ (PP-RCT)	4" (110mm) SDR9	85.4 lbs	1 mm	Almost Zero	138 seconds	7 seconds	85.4 lbs	12.3 min
Watertec™ (PP-RCT)	5" (125mm) SDR9	110.2 lbs	1 mm	Almost Zero	155 seconds	8 seconds	110.2 lbs	13.7 min
Watertec™ (PP-RCT)	6" (160mm) SDR11	150.6 lbs	1 mm	Almost Zero	161 seconds	8 seconds	150.6 lbs	14.2 min
Chem Prolok® (PE)	1" X 3" (32mm X 90mm) SDR11X11	85.4 lbs	1.5 mm	Almost Zero	82 seconds	6 seconds	85.4 lbs	8.6 min
Chem Prolok® (PE)	2" X 4" (63mm X 110mm) SDR11X33	76.3 lbs	0.5 mm	Almost Zero	58 seconds	5 seconds	76.3 lbs	6.3 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Chem Prolok® (PE)	3" X 6" (90mm X 160mm) SDR11X33	152.6 lbs	1 mm	Almost Zero	82 seconds	6 seconds	152.6 lbs	8.6 min
Chem Prolok® (PE)	1" X 4" (32mm X 110mm) SDR11X33	53.8 lbs	0.5 mm	Almost Zero	34 seconds	5 seconds	53.8 lbs	5.0 min
Chem Prolok® (PE)	2" X 6" (63mm X 160mm) SDR11X33	116.7 lbs	1 mm	Almost Zero	58 seconds	5 seconds	116.7 lbs	6.3 min
Duo-Pro® Halar®XHalar® (ECTFE)	1" X 3" (32mm X 90mm) SDR21X21	27.0 lbs	0.5 mm	Almost Zero	34 seconds	4 seconds	27.0 lbs	6.0 min
Duo-Pro® Halar®XHalar® (ECTFE)	1" X 4" (32mm X 110mm) SDR21X21	38.0 lbs	0.5 mm	Almost Zero	40 seconds	4 seconds	38.0 lbs	7.0 min
Duo-Pro® Halar®XHalar® (ECTFE)	2" X 4" (63mm X 110mm) SDR21X21	44.0 lbs	0.5 mm	Almost Zero	40 seconds	4 seconds	44.0 lbs	7.0 min
Duo-Pro® Halar®XHalar® (ECTFE)	3" X 6" (90mm X 160mm) SDR21X21	103.0 lbs	1 mm	Almost Zero	117 seconds	4 seconds	103.0 lbs	11.0 min
Duo-Pro® PRO150X150 (PP)	1" X 3" (32mm X 90mm) SDR11X11	56.2 lbs	1 mm	Almost Zero	94 seconds	6 seconds	56.2 lbs	8.6 min
Duo-Pro® PRO150X150 (PP)	2" X 4" (63mm X 110mm) SDR11X11	96.7 lbs	1 mm	Almost Zero	113 seconds	7 seconds	96.7 lbs	10.2 min
Duo-Pro® PRO150X150 (PP)	3" X 6" (90mm X 160mm) SDR11X11	200.1 lbs	1 mm	Almost Zero	161 seconds	8 seconds	200.1 lbs	14.2 min
Duo-Pro® PRO150X150 (PP)	1" X 4" (32mm X 110mm) SDR11X11	78.7 lbs	1 mm	Almost Zero	113 seconds	7 seconds	78.7 lbs	10.2 min
Duo-Pro® PRO150X150 (PP)	2" X 6" (63mm X 160mm) SDR11X11	175.4 lbs	1 mm	Almost Zero	161 seconds	8 seconds	175.4 lbs	14.2 min
Duo-Pro® PRO150X45 (PP)	2" X 4" (63mm X 110mm) SDR11X33	51.7 lbs	0.5 mm	Almost Zero	68 seconds	6 seconds	51.7 lbs	6.3 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Duo-Pro® PRO150X45 (PP)	3" X 6" (90mm X 160mm) SDR11X33	103.4 lbs	0.5 mm	Almost Zero	94 seconds	6 seconds	103.4 lbs	8.6 min
Duo-Pro® PRO150X45 (PP)	2" X 6" (63mm X 160mm) SDR11X33	78.7 lbs	0.5 mm	Almost Zero	68 seconds	6 seconds	78.7 lbs	6.3 min
Duo-Pro® PVDFXPVDF (PVDF)	1" X 3" (32mm X 90mm) SDR21X33	22.0 lbs	0.5 mm	Almost Zero	68 seconds	3 seconds	22.0 lbs	5.5 min
Duo-Pro® PVDFXPVDF (PVDF)	2" X 4" (63mm X 110mm) SDR21X33	38.0 lbs	0.5 mm	Almost Zero	74 seconds	3 seconds	38.0 lbs	6.0 min
Duo-Pro® PVDFXPVDF (PVDF)	3" X 6" (90mm X 160mm) SDR33X33	69.0 lbs	0.5 mm	Almost Zero	89 seconds	3 seconds	69.0 lbs	8.0 min
Duo-Pro® PVDFXPVDF (PVDF)	1" X 4" (32mm X 110mm) SDR21X33	30.0 lbs	0.5 mm	Almost Zero	74 seconds	3 seconds	30.0 lbs	6.0 min
Duo-Pro® PVDFXPVDF (PVDF)	2" X 6" (63mm X 160mm) SDR21X33	65.0 lbs	0.5 mm	Almost Zero	89 seconds	3 seconds	65.0 lbs	8.0 min
Fluidlok (IPS) (PE)	2" X 4" SDR11X17	108.0 lbs	mm	Almost Zero	67 seconds	3 seconds	108.0 lbs	10.0 min
Fluidlok (IPS) (PE)	3" X 6" SDR11X17	235.0 lbs	mm	Almost Zero	99 seconds	5 seconds	235.0 lbs	16.0 min
Poly-Flo® PE100RC (PE)	1" X 1-1/2" (32mm X 50mm) SDR11X17	25.0 lbs	0.5 mm	Almost Zero	25 seconds	4 seconds	25.0 lbs	4.0 min
Poly-Flo® PE100RC (PE)	2" X 3" (63mm X 90mm) SDR11X17	65.0 lbs	1 mm	Almost Zero	35 seconds	5 seconds	65.0 lbs	8.0 min
Poly-Flo® PE100RC (PE)	4" X 6" (110mm X 160mm) SDR11X17	223.0 lbs	1.5 mm	Almost Zero	80 seconds	7 seconds	223.0 lbs	14.0 min
Poly-Flo® PPR (PP)	1" X 1-1/2" (32mm X 50mm) SDR11X17	15.0 lbs	0.5 mm	Almost Zero	45 seconds	4 seconds	15.0 lbs	3.0 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint

Maxiplast® (Butt) Welding Parameters

CURRENT AS OF
11/18/2020

Product Line & Material	Pipe Size	Initial Melt Pressure	Bead Height	Melt Pressure	Heatsoak Time	Changeover Time	Welding Pressure	Cooling Time
Poly-Flo® PPR (PP)	2" X 3" (63mm X 90mm) SDR11X17	60.0 lbs	0.5 mm	Almost Zero	80 seconds	6 seconds	60.0 lbs	9.0 min
Poly-Flo® PPR (PP)	4" X 6" (110mm X 160mm) SDR11X17	185.0 lbs	1 mm	Almost Zero	150 seconds	7 seconds	185.0 lbs	17.0 min



Please visit the Asahi Weld App
at www.asahi-america.com for
up to date weld parameters

Welding Temperatures

PP: 393°F - 410°F (200°C - 210°C)
 PE: 420°F - 446°F (215°C - 230°C)
 PVDF: 436°F - 446°F (225°C - 230°C)
 ECTFE: 527°F - 536°F (275°C - 280°C)

A reduction in the cooling time of up to 50%, i.e. removal of the welded part from the welding machine, is permitted in the following circumstances:

- the joint connection was created under workshop conditions and
- the removal of the part from the welding machine and its temporary storage until the complete cooling time according to the Cooling Time column causes negligible loading of the joint